

## **SiwoPUD-1219**

**Characteristics:** Cationic, aqueous, aliphatic polyurethane dispersion based on polyether.

**Supplied as:** 30% in water

<b>Physical characteristics:</b>	Appearance	Translucence
	Non-volatile constituent	30±1 %
	Ionicity	Cationic
	PH value	3.5- 5.5
	Viscosity	≤50 mPa s
	Mean particle size	≤100 nm
	Organic solvent	5%
	Glass transition temperation Tg	-30°C
	Elongation	250-300%
	Tensile strength	6.7Mpa
	Elasticity modulus (100% )	4.2Mpa
	Shear stability	good
	Yellowing resistance	non- yellowing

**Storage:** The dispersion should be stored in a frost-free place in tightly sealed containers. It contains no preservative.

**Application:** Cationic polyurethane aqueous dispersion with high molecular weight. The coating film has medium hardness, excellent hydrolysis resistance and water resistance. Mainly used for metal surface treatment, fabric printing primer coat, and other coatings.

The information and recommendations in this publication are to the best of our knowledge, information and belief accurate at the date of publication. Nothing herein is to be construed as a warranty, express or otherwise. In all cases, it is the responsibility of the users to determine the applicability of such information or suitability of any products for their own purposes. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such is free of patent infringement and are not recommendations to infringe on any patent.