

## SiwoPUD-<sup>®</sup>EC-200

**Characteristics:** Hydrophilic, aliphatic polyisocyanate.

**Supplied as:** 100%

<b>Physical characteristics:</b>	Appearance	Transparent
	Non-volatile constituent(%)	100
	Ionicity	Containing sulfonate
	NCO content (%)	16.0 ± 1
	Viscosity (mPa·s )	2000-5000
	Density(d <sub>4</sub> <sup>20</sup> )	1.09
	Monomeric diisocyanate content	≤0.2%

**Storage:** The crosslinker should be stored in tightly sealed containers, protected against frost and away from direct sunlight.

**Application:** Sulfonate modified water-dispersed polyisocyanate, high crosslinking density, fast drying, high gloss. It is mainly used in water-based coatings, water-based adhesives, etc. It can be diluted with propylene glycol methyl ether acetate (PMA).

The information and recommendations in this publication are to the best of our knowledge, information and belief accurate at the date of publication. Nothing herein is to be construed as a warranty, express or otherwise. In all cases, it is the responsibility of the users to determine the applicability of such information or suitability of any products for their own purposes. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such is free of patent infringement and are not recommendations to infringe on any patent.