

## SiwoPUD-2411

**Characteristics:** Aqueous, aliphatic polyurethane dispersion based polycarbonate.

**Supplied as:** 32% in water

Physical characteristics: Appearance Translucence

 $\begin{array}{lll} \mbox{Non-volatile constituent} & 32\pm 1~\% \\ \mbox{PH value} & 7.0 - 9.5 \\ \mbox{Viscosity} & \leqslant 100 \mbox{mPa} \cdot \mbox{s} \\ \mbox{Mean particle size} & \leqslant 100 \mbox{ nm} \\ \mbox{NMP, NEP, DMAC} & \mbox{Free} \\ \end{array}$ 

Elongation 550-650%
Tensile strength 46.8Mpa
100%Modulus 9.6Mpa
Shear stability Good
Dry Fast

Yellowing resistance Non- yellowing

**Storage:** The dispersion should be stored in a frost-free place in tightly sealed containers. It

contains no preservative.

**Application:** It has small particle size, high acid value, good ductility and elasticity, and good

water resistance. It is suitable for use as printing ink.

The information and recommendations in this publication are to the best of our knowledge, information and belief accurate at the date of publication. Nothing herein is to be construed as a warranty, express or otherwise. In all cases, it is the responsibility of the users to determine the applicability of such information or suitability of any products for their own purposes. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such is free of patent infringement and are not recommendations to infringe on any patent.