

SiwoPUD® - 8051 HB

Characteristics: Aqueous, aliphatic polyurethane dispersion based on polyether.

Supplied as: 37% in water

Physical characteristics:	Appearance	Translucence
	Non-volatile constituent	37±1 %
	PH value	7.0 - 9.5
	Viscosity	≤500 mPa·s
	Mean particle size	≤100 nm
	Organic solvent	4.5%
	Glass transition temperature Tg	-35℃
	Elongation	900-1000%
	Tensile strength	31.6 Mpa
	100%Modulus	3.1 Mpa
	Shear stability	good
	Dry/touch	≤30min
	Dry/through	≤60min
	Yellowing resistance	non- yellowing

Storage: The dispersion should be stored in a frost-free place in tightly sealed containers. It contains no preservative.

Application: Its coating film exhibits some degree of softness, excellent resilience, excellent water resistance, and low temperature resistance. It has good washing fastness. It can be used in fabric printing and coatings.

The information and recommendations in this publication are to the best of our knowledge, information and belief accurate at the date of publication. Nothing herein is to be construed as a warranty, express or otherwise. In all cases, it is the responsibility of the users to determine the applicability of such information or suitability of any products for their own purposes. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such is free of patent infringement and are not recommendations to infringe on any patent.