

## **SiwoPUD-<sup>®</sup> F130**

**Characteristics:** Aromatic, aqueous polyurethane dispersion based on polyester.

**Supplied as:** 35% in water

<b>Physical characteristics:</b>	Appearance	Translucence
	Non-volatile constituent	35±1 %
	PH value	7.0 - 9.5
	Viscosity	≤300mPa·s
	Mean particle size	≤100 nm
	NMP, NEP, DMAC	Free
	Shore A Hardness	90
	Shear stability	good
	Dry	Fast
	Yellowing resistance	yellowing

**Storage:** The dispersion should be stored in a frost-free place in tightly sealed containers. It contains no preservative.

**Application:** Its film has high hardness, excellent heat and wear resistance. It can be used in wood coating and industrial coatings.

The information and recommendations in this publication are to the best of our knowledge, information and belief accurate at the date of publication. Nothing herein is to be construed as a warranty, express or otherwise. In all cases, it is the responsibility of the users to determine the applicability of such information or suitability of any products for their own purposes. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such is free of patent infringement and are not recommendations to infringe on any patent.